

L28 ANSWER 3 OF 16 CAPLUS COPYRIGHT 2002 ACS  
 AN 1996:624816 CAPLUS  
 DN 125:249556  
 TI Self-extinguishing styrenic resin compositions with dripping during burning  
 IN Yamamya, Rei; Fujita, Tomoyuki  
 PA Asahi Chemical Ind, Japan  
 SO Jpn. Kokai Tokkyo Koho, 6 pp.  
 CODEN: JKXXAF  
 DT Patent  
 LA Japanese  
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 08208939	A2	19960813	JP 1995-16944	19950203 <--
AB	<p>             The title compns. comprise (A) 100 parts rubber-modified styrenic resins, (B) 4-8 parts tetrabromobisphenol A and polyhalogenated aliph. ether deriva., (C) 20-50% (vs. B, B + C .ltoreq.10 parts) polyhalogenated diphenylalkanes, (D) 20-50% (vs. B) Sb2O3, and (E) 0.0005-0.05% (as Si) org. polysiloxanes. Thus, 100 parts polybutadiene-modified polystyrene was kneaded with 4 parts EG 3100, 1 part Saytex 8010, 1 part Sb2O3, and 0.005% T9F 451-100 and injection-molded to obtain a test piece showing Izod impact strength 9 kg-cm/cm, flexural modulus 25,000 kg/cm2, heat distortion temp. 80.degree., UL-94 fire resistance rating V-2, and dripping and good self-extinguishing properties during a flammability test.           </p>				

February 7, 2002